

IWAKI dælur - efnapól

Númer	Vökvi	Efnaformúla	SG	Styrkur %	Hámarks vinnuhiti °C									Hámarks vinnuhiti °C								
					VC	VH	V6	VM	PC	PH	TC	FC	SH	PVC	PPG	PVDF	FKM	EPDM	SUS	HC	Ti	CE
1	Acetaldehyde	CH ₃ CHO			-	-	-	-	-	60	-	-	20	1	60	1	1	60	20	60	20	60
2	Acetaldehyde Aqueous	CH ₃ CHO			-	-	-	-	60	-	-	-	-	1	80	1	60	80	0	0	0	60
3	Acetamide	CH ₃ CONH ₂			-	-	-	-	20	-	-	-	-	1	20	0	20	20	1	1	1	60
4	Acetic Acid	CH ₃ COOH		10	40	20	40	40	40	20	40	60	20	60	80	120	40	60	60	20	20	60
5	Acetic Acid	CH ₃ COOH		20	20	20	40	20	20	20	20	60	20	40	60	120	20	60	40	20	20	60
6	Acetic Acid	CH ₃ COOH		50	20	-	-	20	20	-	20	60	20	40	40	120	20	1	40	20	20	60
7	Acetic Acid	CH ₃ COOH		80	20	-	-	20	20	-	20	40	20	40	20	40	20	1	40	20	20	60
8	Acetic Acid (Glacial)	CH ₃ COOH		98	-	-	-	-	-	-	-	-	-	1	1	1	1	0	1	20	20	60
9	Acetic Anhydride	(CH ₃ CO ₂) ₂ O		Hreint	-	-	-	-	-	-	-	20	20	1	1	20	1	1	20	20	20	60
10	Acetone	CH ₃ COCH ₃			-	-	-	-	-	20	-	-	20	1	40	1	1	40	20	20	20	60
11	Acetone Aqueous	CH ₃ COCH ₃			40	20	20	40	60	20	60	60	20	60	80	120	100	100	20	20	20	60
12	Acetonitrile	CH ₃ CN			-	-	-	-	-	-	-	40	-	0	20	40	0	20	0	0	0	60
13	Acetophenone	C ₈ H ₈ O			-	-	-	-	-	-	-	20	-	0	40	20	1	80	0	0	0	60
14	Acetyl Acetone	CH ₃ COCH ₂ COCH ₃			-	-	-	-	-	-	-	-	20	1	20	1	1	1	20	20	20	60
15	Acetyl Bromid	CH ₃ COBr			-	-	-	-	-	-	-	-	-	0	0	0	60	0	0	0	0	60
16	Acetyl Chloride	CH ₃ COCl			-	-	-	-	-	-	-	40	-	0	40	40	1	1	1	20	20	60
17	Acetylene	C ₂ H ₂			-	-	-	-	60	-	60	60	20	1	80	80	100	1	20	20	20	60
18	Acrylonitrile	CH ₂ =CHCN			-	20	20	-	-	20	-	40	20	20	20	40	1	60	20	20	20	60
19	Acrylic Acid Ethyl Ester				-	-	-	-	-	-	-	40	-	1	0	40	0	0	0	0	0	60
20	Adipic Acid Aqueous	HO ₂ C(CH ₂) ₄ CO ₂ H		Mettað	40	20	-	40	60	20	60	60	-	60	100	60	80	80	1	20	20	60
21	Allyl Chloride	CH ₂ =CHCH ₂ Cl			-	-	-	-	-	-	20	20	-	1	1	20	40	1	0	0	0	60
22	Allyl Alcohol	CH ₂ =CHCH ₂ OH			-	-	-	-	60	-	60	60	20	1	60	80	80	1	20	20	20	60
23	Almiium Acetate	(CH ₃ CO ₂) ₃ Al		Mettað	40	20	20	40	40	20	60	60	20	40	40	120	80	80	20	20	20	60
24	Alminum Bromide	AlBr ₃		Mettað	40	-	-	40	60	-	60	60	-	60	80	120	80	60	0	0	0	60
25	Aluminum Ammonium Sulfate	(NH ₄) ₂ SO ₄ Al ₂ (SO ₄) ₃		Mettað	-	-	-	-	60	-	60	60	-	1	100	120	100	80	40	0	0	60
26	Aluminum Chloride	AlCl ₃		Mettað	40	20	-	40	60	20	60	60	-	60	100	60	100	100	1	20	1	60
27	Aluminum Fluoride	AlF ₃		Mettað	-	-	-	-	-	-	-	-	-	60	80	120	100	80	1	1	20	1
28	Aluminum Hydrooxide	Al(OH) ₃		Mettað	40	-	-	40	60	-	60	60	-	60	100	120	100	100	1	1	20	60
29	Aluminum Nitrate	Al(NO ₃) ₃ ·9H ₂ O		Mettað	40	-	-	40	60	-	60	60	-	60	80	100	100	100	1	1	20	60
30	Aluminum Sulfate	Al ₂ (SO ₄) ₃			40	20	40	40	60	20	60	60	20	60	100	120	60	60	100	20	20	60
31	Amber Acid	COOH(CH ₂) ₂ COOH			40	-	-	40	60	-	60	60	-	60	100	120	100	100	0	0	0	60
32	Ammonia Gas	NH ₃		100	-	20	20	-	-	20	-	60	20	60	100	120	1	80	20	20	20	60
33	Ammonia Liquid	NH ₃			-	-	-	-	-	20	-	60	20	1	40	120	1	60	20	20	20	60
34	Ammonia Water	NH ₄ OH		10	20	20	20	20	20	20	20	60	20	60	100	120	20	100	20	20	1	60
35	Ammonium Acetate	CH ₃ COONH ₄		Mettað	40	-	20	40	60	-	60	60	-	60	60	120	100	100	20	0	0	60
36	Ammonium Bromide	NH ₄ Br		Mettað	-	-	-	-	-	-	-	-	-	0	0	0	20	0	1	20	20	60
37	Ammonium Carbonate	(NH ₄) ₂ CO ₃		Mettað	40	20	40	40	60	20	60	60	20	60	100	120	100	100	120	20	20	60
38	Ammonium Chloride	NH ₄ Cl		Mettað	40	20	40	40	60	20	60	60	20	60	100	80	100	100	40	20	20	60
39	Ammonium Copper				-	-	-	-	20	-	-	-	-	0	20	0	20	20	0	0	0	60
40	Ammonium Difluoride	NH ₄ HF		Mettað	40	-	-	40	60	-	60	60	-	60	80	120	100	100	1	0	0	60
41	Ammonium Fluoride	NH ₄ F		20	40	-	-	40	60	-	60	60	-	40	80	120	60	60	1	1	0	60
42	Ammonium Hydrogencarbonate	NH ₄ HCO ₃		40	-	-	-	-	20	-	-	-	-	0	20	0	20	20	20	0	0	60
43	Ammonium Hydrogensulfite	NH ₄ HSO ₄		40	20	-	-	20	20	-	-	-	20	20	20	0	20	1	20	20	20	60
44	Ammonium Hydroxide	NH ₄ OH		40	20	-	-	20	20	-	20	60	-	60	100	120	20	60	0	0	0	60
45	Ammonium Magnesium Sulfate				-	-	-	-	20	20	20	20	20	0	20	20	20	20	20	20	20	60
46	Ammonium Metaphosphate	NH ₄ PO ₃			40	-	-	40	60	-	60	60	-	60	100	120	80	80	0	0	0	60
47	Ammonium Nitrate	NH ₄ NO ₃			40	-	40	40	60	-	60	60	-	60	100	120	80	80	40	1	1	60
48	Ammonium Oxalate	(NH ₄) ₂ C ₂ O ₄ ·H ₂ O			-	-	-	-	-	-	-	20	-	0	20	20	0	20	1	1	0	60
49	Ammonium Perchlorate	NH ₄ CLO ₄			-	-	-	-	-	-	-	20	-	20	0	20	0	0	1	1	20	60

Númer	Vökvi	Efnaformúla	SG	Styrkur %	Hámarks vinnuhiti °C									Hámarks vinnuhiti °C								
					VC	VH	V6	VM	PC	PH	TC	FC	SH	PVC	PPG	PVDF	FKM	EPDM	SUS	HC	Ti	CE
208	Diethylene Glycol				20	-	-	20	20	-	20	20	20	20	20	20	20	20	20	60		
209	Diethylether	C ₂ H ₅ OC ₂ H ₅		Hreint	-	-	-	-	-	-	-	-	40	-	-	-	-	-	-	60		
210	Diethylene Triamine	H ₅ N(CH ₂ CH ₂ NH) ₂ H			-	-	-	-	-	-	-	20	40	20	-	-	-	-	60			
211	Diglycolic Acid	(HO ₂ CCH ₂) ₂ O+H ₂ O		Mettað	20	-	-	20	20	-	20	20	-	-	-	-	-	-	60			
212	Diisobutylene	C ₈ H ₁₆		Hreint	-	-	-	-	-	-	-	40	60	20	-	-	-	-	60			
213	Diisobuty Keton	[(CH ₃) ₂ CHCH ₂] ₂ CO		Hreint	-	-	-	-	-	-	-	-	-	20	-	-	-	-	60			
214	Diisoprppyl Ketone	[(CH ₃) ₂ CH ₂] ₂ CO		Hreint	-	-	-	-	-	-	-	-	-	-	-	-	-	-	60			
215	Dimethyl Amine	(CH ₃) ₂ NH			-	-	-	-	20	-	20	20	-	-	-	-	-	-	60			
216	Dimethyl Aniline	C ₈ H ₁₁ N			-	-	-	-	-	-	-	-	20	20	-	-	-	-	60			
217	Dimethyl Formamide	HCON(CH ₃) ₂			-	-	-	-	-	-	-	-	-	-	-	-	-	-	60			
218	Dimethyl Phthalate	C ₆ H ₄ (COOCH ₃) ₂			-	-	-	-	-	-	-	20	20	-	-	-	-	-	60			
219	Dimethyl Sulfate	(CH ₃ O) ₂ SO ₂			-	-	-	-	-	-	-	-	-	20	-	-	-	-	60			
220	Dimethyl Sulfoxide	(CH ₃) ₂ SO			-	-	-	-	-	-	-	-	-	-	-	-	-	-	60			
221	Dimetry Acetaminade	CH ₃ CON(CH ₃) ₂			-	-	-	-	-	-	-	-	-	-	-	-	-	-	60			
222	Diocetyl Phthalate	C ₆ H ₄ (COOH ₈ H ₁₇) ₂			-	-	-	-	-	-	-	20	40	-	-	-	-	-	60			
223	Dioxane	C ₄ H ₈ O ₂		Hreint	-	-	-	-	-	-	-	-	-	-	-	-	-	-	60			
224	Dioxolane	C ₃ H ₆ O ₂			-	-	-	-	-	-	-	-	-	-	-	-	-	-	60			
225	Diphenyl	C ₆ H ₅ -C ₆ H ₅			-	-	-	-	-	-	-	-	-	20	-	-	-	-	60			
226	Diphenyl Oxide	C ₁₂ H ₈ O		Mettað	-	-	-	-	-	-	-	-	-	-	-	-	-	-	60			
227	Disodium Phosphate	Na ₂ HPO ₄			-	-	-	-	-	-	-	-	60	-	-	-	-	-	60			
228	Epichlorohydrine	C ₃ H ₅ OCl		Hreint	-	-	-	-	-	-	-	-	-	-	-	-	-	-	60			
229	Ethanolamine	H ₂ NCH ₂ CH ₂ OH		Hreint	-	-	-	-	20	20	-	-	-	20	-	-	-	-	60			
230	Ether	C ₂ H ₅ O			20	-	-	20	-	-	-	-	-	-	-	-	-	-	60			
231	Ethyl Acetate	CH ₃ COOC ₂ H ₅			-	-	-	-	-	-	-	-	20	-	-	-	-	-	60			
232	Ethyl Acetoacetate	CH ₃ CO-CH ₂ COOC ₂ H ₅		Hreint	-	-	-	-	-	-	-	-	40	-	-	-	-	-	60			
233	Ethyl Acrylate	H ₂ CCH-COOC ₂ H ₅		Hreint	-	-	-	-	-	-	-	-	40	-	-	-	-	-	60			
234	Ethyl Alcohol	C ₂ H ₅ OH			40	40	30	40	60	80	60	60	30	-	-	-	-	-	60			
235	Ethyl Benzene	C ₆ H ₅ C ₂ H ₅			-	-	-	-	-	-	-	20	60	-	-	-	-	-	60			
236	Ethyl Chloride	C ₂ H ₅ Cl			-	-	-	-	-	-	-	60	60	-	-	-	-	-	60			
237	Ethyl Ether	(C ₂ H ₅) ₂ O		Hreint	-	-	-	-	-	-	-	-	40	20	-	-	-	-	60			
238	Ethyl Formate	HCOOC ₂ H ₅		Hreint	-	-	-	-	-	-	-	-	-	-	-	-	-	-	60			
239	Ethyl Hexanol	CH ₃ (CH ₂) ₃ CH(C ₂ H ₅)CH ₂ OH			-	-	-	-	20	-	20	60	-	-	-	-	-	-	60			
240	Ethyl Mercaptan	C ₂ H ₅ -SH		Hreint	-	-	-	-	-	-	-	-	-	-	-	-	-	-	60			
241	Ethyl Oxalate	(CO ₂ C ₂ H ₅) ₂			-	-	-	-	-	-	-	-	-	-	-	-	-	-	60			
242	Ethylalcohol	C ₂ H ₅ OH		Hreint	40	-	-	40	60	-	60	60	-	-	-	-	-	-	60			
243	Ethylen Chrohydrin	ClCH ₂ -CH ₂ OH		Hreint	-	-	-	-	-	-	-	-	40	-	-	-	-	-	60			
244	Ethylene Acrylate				-	-	-	-	-	-	-	-	20	20	-	-	-	-	60			
245	Ethylene Bromide	CH ₂ Br-CH ₂ Br			-	-	-	-	-	-	-	-	60	-	-	-	-	-	60			
246	Ethylene Chloride	ClCH ₂ CH ₂ Cl			-	-	-	-	-	-	-	20	60	-	-	-	-	-	60			
247	Ethylene Diamine	NH ₂ CH ₂ CH ₂ NH ₂		Hreint	-	-	-	-	-	-	-	-	20	-	-	-	-	-	60			
248	Ethylene Dibromide	(CH ₂ Br) ₂			-	-	-	-	-	-	-	20	60	20	-	-	-	-	60			
249	Ethylene Glycol	CH ₂ OH-CH ₂ OH		Hreint	40	20	-	40	60	20	60	60	-	-	-	-	-	-	60			
250	Ethylene Oxido	(CH ₂) ₂ O		Hreint	-	-	-	-	-	-	-	-	40	20	-	-	-	-	60			
251	Ethylene Trichloride	C ₂ HCl ₃			-	-	-	-	-	-	-	-	20	20	-	-	-	-	60			
252	Fatty Acid	RCOOH			20	-	-	20	20	-	20	60	20	-	-	-	-	-	60			
253	Ferous Nitrate	Fe(NO ₃) ₂		Mettað	40	-	-	40	60	-	60	60	-	-	-	-	-	-	60			
254	Ferric Chloride	FeCl ₃			40	-	-	40	60	-	60	60	-	-	-	-	-	-	60			
255	Ferric Hydroxide	Fe(OH) ₃		Mettað	40	-	-	40	60	-	60	60	-	-	-	-	-	-	60			
256	Ferric Sulfate	Fe ₂ (SO ₄) ₃			-	-	-	-	-	-	-	-	-	-	-	-	-	-	60			
257	Ferric(Iron) Nitrate	Fe(NO ₃) ₃			40	20	20	40	60	20	60	60	20	-	-	-	-	-	60			
258	Ferrous Chloride	FeCl ₂			-	-	-	-	-	-	-	-	-	-	-	-	-	-	60			
259	Ferrous Sulfate	FeSO ₄			-	-	-	-	-	-	-	-	-	-	-	-	-	-	60			
260	Ferrous(Iron) Chloride	FeCl ₂			40	-	-	40	60	-	60	60	-	-	-	-	-	-	60			
261	Ferrous(Iron) Hydroxide	Fe(OH) ₂		Mettað	40	-	20	40	60	-	60	60	-	-	-	-	-	-	60			

Númer	Vökvi	Efnaformúla	SG	Styrkur %	Hámarks vinnuhiti °C									Hámarks vinnuhiti °C								
					VC	VH	V6	VM	PC	PH	TC	FC	SH	PVC	PPG	PVDF	FKM	EPDM	SUS	HC	Ti	CE
640	Trichloroacetic Acid	Cl ₃ C·COOH			-	-	-	-	-	-	-	40	-	1	60	40	1	1	1	0	0	60
641	Trichloroethylene	ClHC=CCl ₂			-	-	-	-	20	-	20	60	-	1	20	60	20	1	0	0	0	60
642	Trichloroethylene	C2HCℓ3			-	-	-	-	-	-	-	-	-	0	0	0	0	0	0	0	0	60
643	Triethanolamine	N(CH ₂ CH ₂ OH) ₃			-	-	-	-	-	-	-	-	20	1	1	1	1	20	20	20	20	60
644	Triethyl Propan				-	-	-	-	-	-	-	60	-	0	0	80	0	0	0	0	0	60
645	Triethylamine	(C ₂ H ₅) ₃ N			-	20	20	-	-	20	-	20	20	20	20	20	1	20	20	20	20	60
646	Trisodium Phosphate	Na ₃ PO ₄	1,02	4	-	-	-	-	-	-	-	-	-	0	0	0	0	0	0	0	0	60
647	Turbin Oil				20	-	-	20	20	-	20	20	-	20	20	20	60	1	0	0	0	60
648	Turpentine Oil				-	-	-	-	20	-	20	60	-	0	20	120	20	20	0	0	0	60
649	Uranium Chloride				-	-	-	-	20	-	-	-	-	0	20	0	20	20	1	0	0	60
650	Uranium Oxide				-	-	-	-	20	-	20	20	-	0	20	20	20	20	0	0	0	60
651	Urea	CO(NH ₂) ₂		Hreint	20	20	20	20	20	20	20	60	20	60	100	120	20	20	20	20	20	60
652	Uric Acid	C ₅ H ₄ N ₄ O ₃			-	-	-	-	-	-	-	-	20	0	0	0	0	20	20	20	20	60
653	Urine			80	40	-	-	40	60	-	60	60	-	60	80	120	100	100	0	0	0	60
654	Vaseline				20	-	-	20	20	-	20	60	-	60	80	120	20	1	0	0	0	60
655	Vegetable Oil				20	-	20	20	20	-	20	60	-	20	20	120	20	20	0	0	0	60
656	Vineger				40	20	20	40	60	20	60	60	20	60	100	120	60	60	20	20	20	60
657	Vinyl Acetate	CH ₃ COOCH=CH ₂			-	-	-	-	-	-	-	60	20	1	0	120	1	20	20	20	20	60
658	Whisky				40	20	20	40	60	20	60	60	20	60	60	120	60	80	20	20	20	60
659	White Acid			Hreint	-	-	-	-	-	-	-	60	-	0	0	80	0	0	0	0	0	60
660	White Liiquor				40	-	-	40	40	-	40	60	-	60	60	120	40	80	0	0	0	60
661	Wine				40	-	-	40	40	-	40	60	-	60	60	120	40	80	0	0	0	60
662	Xylene	C ₆ H ₄ (CH ₃) ₂			-	-	-	-	-	-	20	60	20	1	1	80	20	1	20	20	20	60
663	Yellow Phoshorus	P ₄			-	-	-	-	-	-	-	60	-	20	20	120	0	0	0	0	0	60
664	Zinc Acetate	(CH ₃ COO) ₂ Zu			40	-	-	40	60	-	60	60	-	60	100	120	100	80	0	0	0	60
665	Zinc Bromide	ZnBr ₂			40	-	-	40	60	-	60	60	-	60	80	80	60	60	0	0	0	60
666	Zinc Chloride	ZnCl ₂			40	-	-	40	60	-	60	60	-	60	80	80	60	60	0	0	0	60
667	Zinc Nitrate	Zn(NO ₃) ₂ ·6H ₂ O			40	-	-	40	60	-	60	60	-	60	100	120	100	80	0	0	0	60
668	Zinc Sulfate	ZnSO ₄			40	-	40	40	60	-	60	60	-	60	100	120	100	80	100	0	0	60